



Anti-Corrosion

INOX 200

PROTECTIVE COATING FOR STAINLESS STEEL

Inox 200 is a single component protective coating with the look of Stainless Steel. Inox 200 forms a flexible protective natural film which, when dry, matches the surface finish of Stainless Steel. Inox 200 is especially effective for the cosmetic touch-up of damaged/repaired Stainless Steel, particularly discoloration due to high temperature welding.

With unique combination of flexibility and hardness, it provides a closed durable film. Totally free of lead. The aerosol uses LPG propellant for controlled spray and optimum film properties.

PRODUCT CODES / FILL SIZES



30299 / 400ml

APPLICATIONS

Touch up of discoloration on stainless steel, due to heat (as from welding).

- Safety equipment
- Piping and couplings
- Containers
- Furniture, home and garden equipment
- Machinery construction and industrial vehicles
- Building and metallic structures

DIRECTIONS

- Do not use on energized equipment. Use in well ventilated area.
- Shake aerosol can well for at least one minute after agitator ball is free. Repeat frequently while using.
- Apply to a clean, degreased, dry surface for best results. Remove rust and scale with a wire brush.
- Apply in light, even coats; best results are obtained with 2 lighter rather than 1 heavy coat.
- Additional coats can be applied after 5 minutes.
- When spraying is finished, clean aerosol valve by turning can upside down and press button until only propellant escapes.
- If clogging occurs, remove button and clean orifice with a fine wire.

Note: For welding purposes it is always better to use a stainless steel alloy with low carbon content such as 304L or 306L. These types of alloys maintain a good natural barrier against corrosion.

TECHNICAL DATA (WITHOUT PROPELLANT)

Appearance	Lustre aspect of stainless steel
Specific Gravity (ASTM D891-59)	1.0 g/cm ³
Solid Content (ASTM D-1644 ISO 1515)	30 ± 2 %
Pigment	stainless steel powder composed of 17% Cr, 13% Ni, 2.25% Mo, 67.75% Fe
Coverage (40 µm dry film)	2.5 m ² /can
Application Conditions	
Minimum Ambient Temperature	8°C
Minimum Surface Temperature	5 °C
Maximum Humidity	85% RH
Drying Time	
Dry-To-Touch	10 minutes
Totally Dry	30 minutes
Adhesion on Galvanized Steel (ASTM D3359)	0 B
Heat Resistance (ASTM D2485-68.)	Approx. 300°C

MATERIALS COMPATIBILITY

OK	-
CAUTION	-
NOT OK	-

STORAGE & SHELF LIFE

The product may be stored at normal ambient temperatures and has a shelf life of not less than 2 years with correct storage. Aerosols should always be stored below 50°C, away from direct heat and naked flame.

HEALTH AND SAFETY

A separate Safety Data Sheet (SDS) according to EC Regulation 73/404/EEC and 648/2004/EC is available from Ambersil.com or via info.uk@crcind.com

MISREPRESENTATION ACT 1967

TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

Version 2.0
Created: July 2019
Updated: N/A

CRC Industries UK Ltd.
Wylde Road, Bridgwater
Somerset, TA6 4DD
United Kingdom

t +44 (0)1278 727200
f +44 (0)1278 425644
e sales.uk@crcind.com
w www.ambersil.com

Company Registered No. 04910479

VAT No. GB 821 5195 42

