

Rustilo DWX 30

Dewatering corrosion preventive

Description

Castrol Rustilo™ DWX 30 is a powerful solvent deposited corrosion preventive with excellent dewatering properties. The solvent, after evaporation, leaves an ultra-thin greasy protective film.

Application

Rustilo DWX 30 rapidly removes water from components subsequent to electroplating processes, after machining using soluble cutting fluids, or parts that have been washed. The very thin residual film provides effective medium term protection against corrosion during intermediate storage or transportation. Rustilo DWX 30 can also be used as a lubricant for mild press working, where corrosion protection without further treatment is required. Although Rustilo DWX 30 can be applied by brushing or spraying, its dewatering action is most effective if the articles to be protected can be immersed in a dip tank.

Advantages

- Excellent water displacing and penetrating properties - can be used for displacing water from the most intricate assemblies with shorter-than-usual dipping times.
- Forms an ultra-thin, even film, which does not interfere with air gauge or light refractory measuring equipment; therefore it need not be removed from components subject to inspection.
- Effectively suppresses fingerprint corrosion on bright steel and finely finished metal components during Manufacture.
- High stability against acidic and alkaline contaminations enables long bath - lifetimes.
- Low drying time guarantees high productivity level.
- Economical in application through large film coverage.

Typical Characteristics

Name	Method	Units	Value
Appearance	Visual	-	Light Brown Liquid
Density @ 15 °C	ASTM D 4052	kg/m	0.800
Flash Point	DIN 51755	°C	> 38
Film Type	-	-	Ultra thin, greasy
Total Film Forming Content	-	%	8
Film Thickness	-	µm	0.6 - 1.0
Consumption	-	kg/100 m	0.8 - 1.2
Corrosion Protection	Indoor Storage	month	8 - 12
	Outdoor Storage	month	3 - 6
Drying time @ 20 °C	-	minutes	30

Additional Information

- The claims on film thickness and consumption are average values. These are valid for smooth surfaces with good drain-off characteristics and simple geometries without holes or recesses.
- "Indoor storage" describes the storage of ferrous components in closed store-rooms having a relative humidity of 60%. Increased protection times could be achieved when treating finished surfaces or store the parts in a sealed pack.
- "Outdoor storage" describes open storage, which assumes primary protection from the elements by tarpaulin or other form of cover.
- Influence of temperature may cause some cloudiness, which is reversible and doesn't have an impact on product quality.
- If required protective films of Rustilo DWX 30 can easily be removed by using a petroleum solvent or alkaline process cleaner, all available from Castrol.

Approvals

Rolls-Royce CSS 122

Rustilo DWX 30
04 Sep 2015
Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol (UK) Limited, PO BOX 352, Chertsey Road, Sunbury On Thames, Middlesex, TW16 9AW
Orders/Enquiries: 0345 9645111 Technical Enquiries: 0345 082 1719
www.castrol.com/industrial