



HIGH LOAD ASSEMBLY PASTE WITH MoS2 MOLY TECH AP

Product Overview

Moly Tech AP is an extreme load, low friction paste for assembly and running in, under the most severe conditions. The high concentration of MOS2 effectively prevents scuffing caused by metal-to-metal contact.

Features and Benefits

- Eliminates seizure, pick-up, wear and scuffing under extreme loads and temperatures
- Gives trouble free assembly and dismantling of all machine components
- Long life lubricating film reducing frictional forces particularly when running-in
- Only minimal application is required

Typical Applications

General assembly and lubrication of all load bearing and sliding surfaces such as splines, cams, threads, keys and wedges, liners and brushes etc.

Directions for Storage and Use

Product is to be stored in a clean, dry, storage area in its original sealed packaging.

Shelf Life (unopened) – 3 years approx *

*Some bleeding may occur, thorough mixing will homogenise the mixture to its original state.

Product can be applied by brush, applicator or automatic lubrication system.

Do not mix with other lubricants if compatibility is not known, for best results purge system of other lubricants. Apply to clean, dry parts only

Disclaimer

The data sheet is based on personal knowledge and experience and is given as a guideline to its possible uses. It does not take into account variables or conditions out of our control that can affect our product in any way. It is the users' sole responsibility to ensure that the product is suitable for the purpose for which it is being used and this data does not in any way form a warranty. If you are unsure of its suitability please contact us and we will be happy to discuss your needs and supply a sample for testing if required. New Tech Lubes Ltd is committed to supplying the best products and may therefore change the information in this specification at any time.

Available Sizes
100gm Tube
500gm Pot
400ml Cart
5kg Tub

Available Grades

Physical Characteristics	
Appearance	Grey Paste
Base	Bentone
Penetration (IP50)	275 – 295
Solids content	50%
Drop Point	None (non melting)
Temperature Range	-60°C - 650°C
Density	1500 kg/m3

Safety Data Sheets

Safety data sheets are available for download from our website, scan the QR code to take you to our website



www.newtechlubes.com